



DECOMIN EPOXY TRANSPARENT FLOOR COATING

PRODUCT DESCRIPTION

IT IS EPOXY BASED , TWO COMPONENT , SOLVENT FREE , TRANSPARENT , FAST CURING UV- RESISTANT TOPCOAT COVERING MATERIAL.

APPLICATION

COATING SURFACE TO BE APPLIED SHOULD BE FREE FROM ADHESION INHIBITING AGENT SUCH AS DUST, DIRT AND OIL . APPLICATION SHOULD BE CARRIED OUT WITHIN RECOATING PERIOD OF THE COATING SYSTEM . IN CASES WHEN APPLICATION IS CARRIED OUT ON AN OLD COATING , THEN YOU SHOULD CONSULT OUR TECHNICAL SERVICE FOR APPLICATION METHOD TENSILE STRENGTH OF THE SURFACE TO BE APPLIED SHOULD BE 1,5 N / MM² AND ITS HUMIDITY SHOULD BE MAXIMUM 4 % . IT SHOULD BE TAKEN INTO ACCOUNT THAT GROUND TEMPERATURE SHOULD BE 3 % MORE THAN DEW POINT .

AREAS OF APPLICATION

IT IS USED INSIDE BUILDINGS , COLORED QUARTZ NONSLIP COATINGS , UV – RESISTANT TOPCOAT TRANSPARENT COVERING SYSTEMS.

PRODUCT FEATURES AND ADVANTAGES

- EASY TO APPLY
- TRANSPARENT
- RESISTANT TO UV AND WEATHER CONDITIONS
- LOW VISCOSITY
- SOLVENT FREE
- MECHANICAL RESISTANCE IS HIGH



RESISTANT TO WATER , SEA WATER WASTEWATER , ALKALIS ,SALTWATER , MINERAL OILS AND FUELS

MIXTURE

IT IS PROVIDED IN THE FROM OF SETS READY TO USE ACCORDING TO THE MIXING RATIO . PLEASE MAKE SURE THAT , BEFORE MIXING , THE TEMPERATURE OF THE PRODUCT IS BETWEEN + 15 / 25°C .

ITS SHOULD BE WELL MIXED FOR ABOUT 3-4 MINUTES WITHOUT DRAGGING AIR INTO IT WITH 300-400 RPM MIXER WHERE A COMPONENT EPOXY / POLYURETHANE RESIN MIXING IS INSTALLED ON THE TIP . LATER , WHOLE OF THE B COMPONENT SHOULD BE DISCHARGED IN TO THE COMPONENT A AND SPECIAL ATTENTION SHOULD BE PAID THAT THERE IS NOT MATERIAL IN COMPONENT B.

5005 ; A+B SHOULD BE MIXED AT LEAST 3 MINUTES UNTIL GETTING HOMOGENEOUS MIXTURE . INGREDIENTS AT THE EDGE AND FLOOR OF THE MIXING VESSEL SHOULD BE THOROUGHLY MIXED . THE MATERIAL IN FIRST MIXING VESSEL SHOULD BE TAKEN INTO A CLEAN CONTAINER AND SHOULD REST FOR A WHILE AND AFTER ABOUT 1 MINUTE LATER IT SHOULD BE MIXED AGAIN AND THEN APPLIED.

MIXTURE

IT SHOULD BE STORED IN UNOPENED PACKAGING, COLD AND DRY PLACE , PROTECTED FROM FROST . FOR SHORT PERIOD STORAGE, MAXIMUM 3 PALETTES CAN BE PUT OVERLAPPED AND SHIPMENT SHOULD BE DONE ACCORDING TO THE SYSTEM OF FIRST IN FIRST OUT. AND FOR LONG PERIOD STORAGE , THE PALETTES SHOULD NOT BE PUT OVERLADPED. IT IS 12 MONTHS FROM THE DATE OF PRODUCTION WIHT PROPER STORAGE CONDITIONS. OPENED PACKAGING SHOULD BE USED WITHIN PROPER STORAGE CONDITIONS . OPENED PACKAGING SHOULD BE USED WITHIN 1 WEEK STORED IN APPROPRIATE STORAGE CONDITIONS.